

SEALING

- **Novamax Technologies (Aust) Pty Ltd**
- **Seal Quality of Universal Anodisers anodising**
- **Australian Standard 2039.2.5-1978**

Require a weight loss of less than 30mg/dm

- **Sealing test as a result as per ISO3270-1974, of 1.91mg/sqdm of you Universal Hardcoat™ sample**
- **Date range from 1.5 - 2.5mg**
- **Typical commercial anodising should give sealing results from 1.0 - 30mg/sqdm. Your results to date suggest sealing of the highest quality.**

Full details of all tests are available on request